

Black Pearl NR - Sun-Gard Automotive Window Film



1/4 inches = 6 mm	Shading Coeff.	Total Solar Energy Reject	Solar Reflect	Solar Absorb	Solar Transmit	Visible Light Reflect (Ext.)	Visible Light Transmit	UV Trans.	Emissivity	"U" Value (S)	"U" Value (Wm)	"U" Value (Ws)	Heat Reduction	Glare Reduction
Black Pearl NR 05	0.680	40.80%	5.50%	50.80%	43.70%	4.50%	4.40%	<1%	0.86	0.95	1.02	1.03	28.3%	95.0%
Black Pearl NR 20	0.710	38.20%	5.50%	47.00%	47.50%	4.70%	19.10%	<1%	0.86	0.95	1.02	1.03	25.1%	78.3%
Black Pearl NR 35	0.790	31.30%	5.90%	36.60%	57.50%	5.40%	36.60%	<1%	0.86	0.95	1.02	1.03	16.7%	58.5%
Black Pearl NR 55	0.840	26.90%	6.30%	29.20%	64.50%	6.30%	56.40%	<1%	0.86	0.95	1.02	1.03	11.4%	36.0%
Black Pearl NR 70	0.880	23.40%	6.60%	24.60%	68.80%	7.20%	68.60%	<1%	0.86	0.95	1.02	1.03	7.2%	22.1%

1/8 inches = 3 mm	Shading Coeff.	Total Solar Energy Reject	Solar Reflect	Solar Absorb	Solar Transmit	Visible Light Reflect (Ext.)	Visible Light Transmit	UV Trans.	Emissivity	"U" Value (S)	"U" Value (Wm)	"U" Value (Ws)	Heat Reduction	Glare Reduction
Black Pearl NR 05	0.700	39.10%	5.50%	48.30%	46.20%	4.40%	4.40%	<1%	0.87	0.98	1.04	1.05	30.0%	95.1%
Black Pearl NR 20	0.730	36.50%	5.60%	44.30%	50.10%	4.60%	19.20%	<1%	0.87	0.98	1.04	1.05	27.0%	78.6%
Black Pearl NR 35	0.810	29.50%	6.00%	33.80%	60.20%	5.30%	36.60%	<1%	0.87	0.98	1.04	1.05	19.0%	59.2%
Black Pearl NR 55	0.860	25.20%	6.40%	26.40%	67.20%	6.20%	56.50%	<1%	0.87	0.98	1.04	1.05	14.0%	37.1%
Black Pearl NR 70	0.900	21.70%	6.70%	21.90%	71.40%	7.00%	68.90%	<1%	0.87	0.98	1.04	1.05	10.0%	23.3%

Summary of Seasonal Conditions:

	Summer Day	Mild Winter	Severe Winter
Temperature Inside	75 F / 24 C	68 F / 20 C	70 F / 21 C
Temperature Outside	89 F / 32 C	45 F / 7 C	0 F / -18 C
Solar Intensity	248.2 Btu/hr-ft ²	0 Btu/hr-ft ²	0 Btu/hr-ft ²
Wind Velocity	7.5 MPH / 4.6 KPH	15 MPH / 9 KPH	15 MPH / 9 KPH

Shading Coefficient calculated under SUMMER DAY conditions.

"U" (S) "U" Value calculated under SUMMER DAY conditions.

"U" (Wm) "U" Value calculated under MILD WINTER conditions.

"U" (Ws) "U" Value calculated under SEVERE WINTER conditions.

Notes:

1. Performance results were generated from testing film applied to 1/4" and 1/8" clear, monolithic, annealed glass. Results have been calculated using the Lawrence Berkeley Lab's "Windows 5.2" software program. Tests, equipment and methods are in accordance with ASTM and NFRC standards. Performance results are subject to variations within industry standards.

2. This data is provided for information purposes only and is not to be considered part of the basis of any bargain or transaction involving Solamatrix, Inc. products. The included data does not constitute a recommendation for, endorsement of, or certification of the product or material tested. Solamatrix, Inc., makes no representation or warranty, expressed or implied, including the implied warranties of merchantability or fitness for a particular purpose, that its products will conform to this test data. Solamatrix's limited warranty should be carefully reviewed prior to purchasing any Solamatrix product. Extrapolation of data from the sample or samples relating to the batch or lot from which data was obtained may not correlate and should be interpreted accordingly with caution. Solamatrix shall not be responsible for variations in quality, composition, appearance, performance, or other features of similar subject matter produced by persons or under conditions over which Solamatrix has no control.