

Madico's

Vision Span 300 White

Optical Properties

Total Solar Energy

Transmitted.....	1%
Reflected	37%
Absorbed.....	62%

Visible Light

Transmitted.....	0%
Reflected	43%

"U" Factor

Median.....	1.10
Design	1.13
Ultraviolet Light Rejected.....	99%
Shading Coefficient	0.21
Total Solar Energy Rejected.....	81%

Physical Properties

Film Thickness	0.002"
Structure	Single-ply
Adhesive Type	Acrylic PSA
Peel Strength	3.5 lbs/inch min
Density	1.43 g/cc
Yield Strength MD/TD	12,000 psi

Test Data

ASTM C-1048 Fallout.....	Pass
--------------------------	------



For More Information

Contact: John Storms, Technical Sales Representative

Phone: 727-812-2550

Cell: 727-512-8763

Email: jstorms@madico.com



MADICO
ISO 9001: 2000 Certified

64 Industrial Parkway, Woburn, MA 01801
800-225-1926 • www.madico.com

*Values cited should be considered nominal values. All information reported to the best of our knowledge.
Independent test results available upon request.*

V0809-R01