


HyTek™ Prime Datasheet

The Next Generation in Protekt® Backsheets

MATERIAL COMPOSITION

TEST:	RESULTS:
Thickness*	250 µm
Width Range	25 – 1700 mm
Weight	320 g/m ²
Density	1.16 g/cm ³
Coating Color Options	White
EVA Color Options	White, Black

FLUORO-COATING / PET / EVA



TECHNICAL CHARACTERISTICS

TEST:	TEST SPECIFICATION(S):	RESULTS:
Tensile Strength at Break (MD)	Internal Testing – Data Available	100 MPa (MD)
Elongation at Break (MD)	Internal Testing – Data Available	135% (MD)
Tear Strength (MD/TD)	Internal Testing – Data Available	4 N (MD) / 4 N (TD)
Dimensional Stability	150°C for 30 min; Internal Testing – Data Available	≤ 1.5%
EVA Peel Strength from Encapsulant	Internal Testing – Data Available	≥ 40 N/cm
Peel Strength of Layers	PET / EVA	≥ 5 N/cm

WEATHERABILITY TESTING PERFORMANCE

TEST:	TEST SPECIFICATION(S):	RESULTS:
Relative Thermal Index (RTI)	Suitable for use at continuous 105°C	125°C
	Suitable for use at continuous 120°C	125°C
Damp Heat Testing	85°C, 85% RH; IEC 61215	3000 Hours
Heat Freeze Humidity	In accordance with UL 1703, >10 cycles	>70% of initial mechanical properties retained
UV Stability	In accordance with UL 746C	>70% of initial mechanical properties retained
MVTR	In accordance with ASTM F1249	≤ 2.5 g/m ² per day

ELECTRICAL INSULATION TESTING PERFORMANCE

TEST:	TEST SPECIFICATION(S):	RESULTS:
Partial Discharge	Internal Data	> 1000 VDC

*Theoretical nominal

This product is covered by one or more U.S. patents and pending U.S. and other patent applications. Please see www.madico.com/patents Typical Data – Not Specification © 2012 Madico, Inc.

Madico PhotoVoltaic Backsheets
64 Industrial Parkway
Woburn MA, 01801
USA

Phone: 1-800-633-0140
Fax: 1-781-935-6841
Email: InfoSF@madico.com
www.madicopv.com

PV0008 R07
MADICO
PV BACKSHEETS