

Madico's

Vision Span 500 Silver Matte Blackout

Optical Properties

Total Solar Energy

Transmitted.....	<1%
Reflected	72%
Absorbed.....	28%

Visible Light

Transmitted.....	0%
Reflected	79%

"U" Factor

Median.....	1.12
Design	1.15
Ultraviolet Light Rejected.....	99%
Shading Coefficient	0.09
Total Solar Energy Rejected.....	92%

Physical Properties

Film Thickness	0.005"
Structure	Two-ply
Adhesive Type.....	Acrylic PSA
Peel Strength.....	3.5 lbs/inch min
Density.....	1.40 g/cc
Yield Strength MD/TD	14,000 psi

Test Data

ASTM C-1048 Fallout.....	Not yet tested
--------------------------	----------------

For More Information



Contact: John Storms, Technical Sales Representative

Phone: 727-812-2550

Cell: 727-512-8763

Email: jstorms@madico.com

*Values cited should be considered nominal values. All information reported to the best of our knowledge.
Independent test results available upon request.*



MADICO
ISO 9001: 2000 Certified

64 Industrial Parkway, Woburn, MA 01801
800-225-1926 • www.madico.com

V0812-R01