


HyTek™ Datasheet

The Next Generation in Protekt® Backsheets

MATERIAL COMPOSITION

TEST:	RESULTS:
Thickness	252 ± 25 µm
Width Range	27 - 1700 mm
Weight	320 ± 32 g/m ²
Density	1.16 g/cm ³
Coating Color Options	White
EVA Color Options	White, Black

FLUORO-COATING / PET / EVA



TECHNICAL CHARACTERISTICS

TEST:	TEST SPECIFICATION(S):	RESULTS:
Tensile Strength at Break (MD)	Internal Testing – Data Available	100 MPa (MD)
Elongation at Break (MD)	Internal Testing – Data Available	135% (MD)
Tear Strength (MD/TD)	Internal Testing – Data Available	9 N (MD) / 15 N (TD)
Dimensional Stability	150°C for 30 min; Internal Testing – Data Available	≤ 1.5%
EVA Peel Strength from Encapsulant	Internal Testing – Data Available	≥ 40 N/cm
Peel Strength of Layers	PET / EVA	≥ 5 N/cm

FLAME RESISTANCE TESTING PERFORMANCE

TEST:	TEST SPECIFICATION(S):	RESULTS:
Flame Spread Index	In accordance with ASTM E162	38

WEATHERABILITY TESTING PERFORMANCE

TEST:	TEST SPECIFICATION(S):	RESULTS:
Relative Thermal Index (RTI)	Suitable for use at continuous 85°C	105°C
Damp Heat Testing	85°C, 85% RH; IEC 61215	2000 Hours
Heat Freeze Humidity	In accordance with UL 1703, >10 cycles	>70% of initial mechanical properties retained
UV Stability	In accordance with UL 746C	>70% of initial mechanical properties retained
MVTR	In accordance with ASTM F1249	≤ 2.5 g/m ² per day

ELECTRICAL INSULATION TESTING PERFORMANCE

TEST:	TEST SPECIFICATION(S):	RESULTS:
Partial Discharge	IEC 60664-1	> 1000 VDC

This product is covered by one or more U.S. patents and pending U.S. and other patent applications. Please see www.madico.com/patents Typical Data – Not Specification © 2012 Madico, Inc.

Madico PhotoVoltaic Backsheets
64 Industrial Parkway
Woburn MA, 01801
USA

Phone: 1-800-633-0140
Fax: 1-781-935-6841
Email: InfoSF@madico.com
www.madicopv.com

PV0007 R03
MADICO®
PV BACKSHEETS