

AQUACER 1039

Paraffin wax emulsion for improved surface characteristics in aqueous coatings and printing inks.

Product Data

Composition

Non-ionic emulsion of modified paraffin wax

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Non-volatile matter:	35 %
Carrier:	Water
Melting point (wax content):	90 °C
Viscosity (23 °C, D=400/s):	35 mPa·s
pH value:	9.5

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Temperature sensitive. To be stored and transported between 5 °C and 35 °C.

Special Note

Intercoat adhesion must be verified in multi-layer systems.

Applications

Liquid Coatings

Special Features and Benefits

The additive has a hydrophobic effect and improves antiblocking. It increases surface slip, scratch and scrub resistance, and creates a soft-feel effect.

Recommended Use

Architectural coatings	<input checked="" type="checkbox"/>
Wood and furniture coatings	<input checked="" type="checkbox"/>

☒ especially recommended ☐ recommended

Recommended Levels

1-6 % additive (as supplied) based on the total formulation – in exceptional cases up to 8 %.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests. The recoatability and intercoat adhesion should be verified in multi-layer systems, particularly at higher doses.

Incorporation and Processing Instructions

The additive should preferably be incorporated at the end of the production process using a low shear rate. Mix well before use.

Printing Inks

Special Features and Benefits

The additive has a hydrophobic effect and improves antiblocking. It increases the surface slip, scratch resistance and scrub resistance.

Recommended Use

For aqueous printing inks and overprint varnishes.

Recommended Levels

3-15 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests. The recoatability and intercoat adhesion should be verified in multi-layer systems, particularly at higher doses.

Incorporation and Processing Instructions

The additive should preferably be incorporated at the end of the production process using a low shear rate. Mix well before use.

Leather Finishes

Special Features and Benefits

The additive has a hydrophobic effect and improves antiblocking. It increases surface slip, scratch and scrub resistances, and creates a soft-feel effect.

Recommended Levels

1-3 % additive (as supplied) based on the total formulation – in exceptional cases up to 4 %.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests. The recoatability and intercoat adhesion should be verified in multi-layer systems, particularly at higher doses.

Incorporation and Processing Instructions

The additive should preferably be incorporated at the end of the production process using a low shear rate. Mix well before use.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYPK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PRIEX®, PURE THIX®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany