

Data Sheet Issue 10/2012

BYK-018

VOC-free silicone-containing defoamer for aqueous pigmented high gloss emulsion systems which is highly effective against microfoam.

Product Data

Composition

Mixture of foam-destroying polysiloxanes and hydrophobic solids

VOC-free (< 1500 ppm)

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (68 °F): 8.30 lbs/US gal

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Separation may occur. Mix well before use.

Applications

Coatings Industry

Special Features and Benefits

BYK-018 is particularly suitable for pigmented high gloss emulsion systems based on styrene acrylate, acrylate or acrylate/polyurethane combinations with a low pigment volume concentration and is very effective against microfoam.

Recommended Levels

0.05-0.8 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Due to its high incompatibility, the defoamer must be incorporated at high shear forces to ensure a good distribution. Otherwise defects may occur in the system.



BYK-018

Data Sheet Issue 10/2012

BYK USA Inc. 524 South Cherry Street P.O. Box 5670 Wallingford, CT 06492

USA Tel 203 265-2086 Fax 203 284-9158

cs.usa@byk.com www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERBYK®, DISPERBYK®, DISPERBYK®, DISPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra. The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.