

DISPERBYK-168

Wetting and dispersing additive for solvent-borne and solvent-free radiation-curable coatings, printing inks and adhesives.

Product Data

Composition

Solution of a high molecular weight block copolymer with pigment affinic groups

Aromatic-free

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Amine value:	10.5 mg KOH/g
Density (68 °F):	9.18 lbs/US gal
Non-volatile matter (20 min., 302 °F):	30 %
Solvents:	Dicarboxylic acid ester
Flash point:	212 °F

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Mix well before use. Separation or turbidity may occur at temperatures below 5 °C (41 °F). Warm to 20 °C (68 °F) and mix well.

Special Note

The treatment of some organic pigments can negatively influence the effectiveness of the additive. In these cases, tests with the untreated pigment of the same type may be successful.

Applications

Coatings Industry

Special Features and Benefits

The additive deflocculates the pigments and stabilizes them by means of steric hindrance. It provides equal electrical charge to the pigment particles. The resulting repulsion and the steric stabilization prevent a possible co-flocculation, which leads to flood and float-free color in pigment mixtures. The deflocculating properties of the additive increase gloss, color strength, transparency, and hiding power and reduce the viscosity of the millbase.

Recommended Use

The additive is recommended for radiation-curable industrial coatings, can coatings and coil coatings.

Recommended Levels

Amount of additive (as supplied) based upon pigment:

Inorganic pigments: 10-15 %
Titanium dioxides: 5-6 %
Organic pigments: 30-90 %
Carbon blacks: 70-140 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

For optimum performance, the additive must be incorporated into the millbase before addition of pigments. The resin and solvent components of the millbase are pre-mixed and then the additive is slowly incorporated while stirring continuously. Do not add the pigments until the additive has been fully distributed.

Printing Inks

Special Features and Benefits

The additive deflocculates the pigments and stabilizes them by means of steric hindrance. It provides equal electrical charge to the pigment particles. The resulting repulsion and the steric stabilization prevent a possible co-flocculation, which leads to flood and float-free color in pigment mixtures. The deflocculating properties of the additive increase gloss, color strength, transparency, and hiding power and reduce the viscosity of the millbase.

Recommended Use

The additive is particularly recommended for UV-curable flexo and offset printing inks. It increases gloss and transparency. DISPERBYK-168 reduces the dispersion time, lowers viscosity and increases color strength.

Recommended Levels

Amount of additive (as supplied) based upon pigment:

Titanium dioxides: 2.5-5 %
Organic pigments, Carbon blacks: 10-20 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

For optimum performance, the additive must be incorporated into the millbase before addition of pigments. The resin and solvent components of the millbase are pre-mixed and then the additive is slowly incorporated while stirring continuously. Do not add the pigments until the additive has been fully distributed.

Adhesives

Special Features and Benefits

The additive deflocculates the pigments and stabilizes them by means of steric hindrance, which leads to a reduction in viscosity and higher transparency. DISPERBYK-168 reduces the dispersion time.

Recommended Use

DISPERBYK-168 is recommended for stabilizing titanium dioxide, organic pigments and carbon blacks in radiation-curable adhesive systems.

Recommended Levels

Amount of additive (as supplied) based upon pigment:

Titanium dioxides: 2.5-5 %
Organic pigments, Carbon blacks: 10-20 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

For optimum performance, the additive must be incorporated into the millbase before addition of pigments. The resin and solvent components of the millbase are pre-mixed and then the additive is slowly incorporated while stirring continuously. Do not add the pigments until the additive has been fully distributed..

DISPERBYK-168

Data Sheet
Issue 10/2012

BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA