

AQUACER 539

Paraffin wax emulsion for improved surface characteristics in aqueous coatings and printing inks.

Product Data

Composition

Non-ionic emulsion of modified paraffin wax

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Non-volatile matter:	35 %
Carrier:	Water
Melting point (wax content):	194 °F
Viscosity (73 °F, D=400/s):	35 mPa·s
pH value:	9.5

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Temperature sensitive. To be stored and transported between 5 °C (41 °F) and 35 °C (95 °F).
Mix well before use.

Special Note

Intercoat adhesion must be verified in multi-layer systems.

Applications

Coatings and Printing Inks

Special Features and Benefits

The additive has a hydrophobic effect and improves antiblocking. It increases surface slip, scratch resistance, abrasion resistance and provides a soft feel effect.

Recommended Use

Architectural coatings	<input checked="" type="checkbox"/>
Wood and furniture coatings	<input checked="" type="checkbox"/>
Printing inks and overprint varnishes	<input checked="" type="checkbox"/>
Leather coatings	<input type="checkbox"/>

☒ especially recommended ☐ recommended

Recommended Levels

1-3 % additive (as supplied) based on the total formulation – in exceptional cases up to 4 %.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests. Recoatability and intercoat adhesion is to be verified in multi-layer systems, particularly if high dosages are used.

Incorporation and Processing Instructions

The additive should preferably be incorporated into the coating at the end of the production process at a low shear rate. Mix well before use.



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA