

# BYK-072

Silicone defoamer for solvent-borne can coatings. Very compatible.  
Suitable as a post-additive for retroactive incorporation.

## Product Data

### Composition

Solution of foam-destroying polysiloxanes

### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (68 °F):	6.95 lbs/US gal
Non-volatile matter (10 min., 302 °F):	1 %
Solvents:	Xylene/n-Butanol/Methyl isobutyl ketone 2/1/1
Flash point:	64 °F

### Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit [www.byk.com](http://www.byk.com) for further information.

## Applications

### Coatings Industry

#### Special Features and Benefits

BYK-072 is a compatible defoamer for solvent-borne formulations. Thanks to its excellent compatibility, this additive can also be used as a post-additive.

#### Recommended use

Recommended for solvent-borne can coatings.

#### Recommended Levels

0.2-1 % additive (as supplied) based upon total formulation.

The dosage levels are indicated for the purpose of orientation. Optimal dosage levels are determined through series of tests.

#### Incorporation and Processing Instructions

The additive can easily be added at any time during coating production.

**BYK USA Inc.**  
524 South Cherry Street  
P.O. Box 5670  
Wallingford, CT 06492  
USA  
Tel 203 265-2086  
Fax 203 284-9158

[cs.usa@byk.com](mailto:cs.usa@byk.com)  
[www.byk.com/additives](http://www.byk.com/additives)

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK® and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER® and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA