

BYK-330

Silicone-containing surface additive with a strong reduction of surface tension of ambient-curing plastic systems. Improves substrate wetting and prevents surface defects.

Product Data

Composition

Solution of a polyether-modified polydimethylsiloxane.

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C):	0.98 g/ml
Non-volatile matter (60 min., 105 °C):	51 %
Solvents:	Methoxypropylacetate
Flash point:	45 °C

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Applications

Ambient-curing Plastic Systems

Special Features and Benefits

BYK-330 is a highly effective silicone additive and provides a strong reduction in surface tension. It thereby improves the wetting of critical substrates such as molds treated with release agents. It also prevents the formation of craters or fish eyes and facilitates the acceptance of spray mist or dust.

Recommended Use

BYK-330 is recommended for systems based on unsaturated polyester resins, such as gel coats.

Recommended Levels

0.1-0.3 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can be incorporated during any stage of the production process, including post-addition. It has proven successful to add the additive at the end of the process to avoid any foam stabilization.

Special Note

Unlike so-called silicone oils, this additive is very user-friendly. Nevertheless, it should be determined in a series of tests whether surface defects occur in certain systems.

BYK-330

Data Sheet
Issue 11/2012

BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735
info@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany