Data Sheet Issue 12/2013

BYKETOL-PC

Additive to reduce drying-out of aqueous pigment concentrates.

Product Data

Composition VOC-free (< 1500 ppm)

Preparation of a modified urea

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C): 1.14 g/ml Refractive index (20 °C): 1.465 Non-volatile matter (10 min., 150 °C): 90 % Solvents: Water

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Applications

Coatings Industry

Special Features and Benefits

The additive is based on a molecular structure which enables the optimum control of water evaporation. This ensures that the aqueous pigment concentrates do not dry-out too quickly. BYKETOL-PC is recommended for use in universal colorants and in pigment concentrates for aqueous coatings.

Recommended Levels

3-10 % additive (as supplied) in pigment concentrates.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can be incorporated during any stage of the production process.

Special Note

It can reduce film hardness at high doses.



BYKETOL-PC

Data Sheet Issue 12/2013







BYK-Chemie GmbH P.O. Box 10 02 45 46462 Wesel

Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERBYK®, DISPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra. This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany