

BYK-1724

VOC-free silicone-containing defoamer for aqueous coatings, printing inks, overprint varnishes, and emulsion adhesives. Compatible defoamer. All-purpose and easy to incorporate.

Product Data

Composition

Emulsion of foam-destroying polysiloxanes, hydrophobic solids and emulsifying agents

VOC-free (< 1500 ppm)
Does not contain
alkylphenol ethoxylates

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (68 °F): 8.43 lbs/US gal
Non-volatile matter (60 min, 221 °F): 27 %
Carrier: Water

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

To be stored and transported between 0 °C (32 °F) and 40 °C (104 °F). Temperature-sensitive emulsion. If the storage temperature drops below or exceeds that recommended, the product should be checked and, if necessary, re-emulsified at room temperature.

Applications

Coatings Industry

Special Features and Benefits

BYK-1724 is recommended for defoaming aqueous coatings based on pure acrylate, acrylate/polyurethane and polyurethane in the pigment volume concentration range (PVC) 0-25. The additive is effective when used in all standard application methods such as rolling, painting, spraying, and pouring.

Recommended Levels

0.1-0.5 % additive (as supplied) based on the total formulation – in exceptional cases up to 1 %.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can generally be added at any time during production. The defoamer should preferably be added to the let-down or be post-added.

Printing Inks and Overprint Varnishes

Special Features and Benefits

BYK-1724 is recommended for defoaming aqueous printing inks and overprint varnishes based on acrylate/polyurethane and polyurethane. Also for aqueous UV systems.

Recommended Levels

0.1-1 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can be added at any time during production. The amount of defoamer used is often divided (by adding 2/3 into the millbase and 1/3 into the let-down or finished product).

Adhesives

Special Features and Benefits

BYK-1724 is recommended for defoaming aqueous dispersion adhesives.

Recommended Levels

0.05-1 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can be added at any time during production.



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYPK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents. This issue replaces all previous versions – Printed in the USA