

BYK-378

Solvent-free silicone surface additive for aqueous, solvent-borne, and solvent-free coatings and adhesives to increase surface slip and to greatly reduce surface tension. Minor foam stabilization and low dosage.

Product Data

Composition

Polyether-modified polydimethylsiloxane

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (68 °F): 8.51 lbs/US gal

Refractive index (68 °F): 1.440

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Applications

Coatings Industry

Special Features and Benefits

The additive greatly increases surface slip and thereby also improves the scratch resistance. It causes a moderate to high reduction in surface tension and thereby excellent substrate wetting and a good anti-cratering effect. Fat edges (picture framing) are avoided. In matted systems it ensures a good orientation of the matting agent.

BYK-378 displays a high effectiveness at low dosage and only stabilizes foam very slightly. It is widely compatible with aqueous, solvent-borne, and solvent-free systems, can be overcoated easily and does not tend to effloresce.

Recommended Use

Architectural coatings	<input type="checkbox"/>
Automotive coatings	<input checked="" type="checkbox"/>
Can coatings	<input type="checkbox"/>
Industrial coatings	<input checked="" type="checkbox"/>
Leather coatings	<input checked="" type="checkbox"/>
Wood and furniture coatings	<input checked="" type="checkbox"/>

☒ especially recommended ☐ recommended

Recommended Levels

0.01-0.3 % additive (as supplied) based on the total formulation, in exceptional cases up to 0.5 %.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can be incorporated during any stage of the production process, including post-addition.

Adhesives**Special Features and Benefits**

The additive causes a moderate to high reduction in surface tension and thereby excellent substrate wetting. It displays a high effectiveness at low dosage and only stabilizes foam very slightly. BYK-378 displays no negative impact on adhesion and does not migrate.

Recommended Use

BYK-378 is used in all common reaction adhesives, for example that are based on polyurethane, epoxy or acrylate.

Recommended Levels

0.01-0.3 % additive (as supplied) based on the total formulation, in exceptional cases up to 0.5 %.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can be incorporated during any stage of the production process, including post-addition.



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PRIEX®, PURE THIX®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25®
are registered trademarks of the BYK group.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA