

DISPERBYK-111

Solvent-free wetting and dispersing additive for solvent-borne and solvent-free coatings and printing inks for stabilizing inorganic pigments, in particular titanium dioxide.
Strong reduction of millbase viscosity.

Product Data

Composition

Copolymer with acidic groups

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Acid value: 129 mg KOH/g

Density (68 °F): 9.68 lbs/US gal

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Mix well before use. Separation and turbidity may occur. Heat to 30-40 °C and stir.

The product should be stored in closed rooms and should not be pre-diluted upon storage.

Special Note

As a result of its high acid value, the additive may potentially accelerate the reaction of baking systems. Check the increase in viscosity during storage.

Applications

Coating Industry and Printing Inks

Special Features and Benefits

The additive deflocculates pigments by means of steric stabilization. As a result of the small particle sizes of the deflocculated pigments, high levels of gloss can be achieved and the color strength is improved. Transparency and hiding power also increase and viscosity is reduced. In this way, the flow characteristics are also improved and high pigment loading is possible. For inorganic pigmented coatings, which are applied using electrostatic high rotation equipment, haze is significantly reduced.

Recommended Use

The additive is recommended for all solvent-borne and solvent-free coatings and printing inks to stabilize inorganic pigments, specifically titanium dioxide. Its anionic character makes it ideal for acid-catalyzed systems (e.g. coil coatings).

Recommended Levels

Amount of additive (as supplied) based upon pigment:

Inorganic pigments: 2.5-5 %

Titanium dioxides: 1-3 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

For optimum performance, the additive must be incorporated into the millbase before addition of pigments.



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SCONA®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents. This issue replaces all previous versions – Printed in the USA