

# SCONA TPPP 9212 GA

Adhesion modifier to improve the mechanical properties of polypropylene filler and glass fiber compounds, polypropylene natural fiber compounds and one-packs in polypropylene.

## Product Data

### Composition

Polypropylene functionalized with maleic acid anhydride (MAH)

### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

MFR (374 °F, 2.16 kg): 80-140 g/10 min

Drying loss (3 h, 230 °F): < 0.5 %

MAH content: ≥ 1,8 %

Supplied as: Granulate

### Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit [www.byk.com](http://www.byk.com) for further information.

### Storage and Transportation

Storage temperature max. 35 °C/95 °F, relative humidity < 80 %. Avoid direct sunlight and contact with water.

### Special Note

The modifier is also available as a powder under the name SCONA TPPP 9212 FA.

## Applications

### Thermoplastics

#### Special Features and Benefits

SCONA TPPP 9212 GA is a highly effective adhesion modifier for polypropylene compounds with short and long glass fibers and fillers (ATH,  $\text{Mg(OH)}_2$ ,  $\text{CaCO}_3$ ) and polypropylene natural fiber compounds – even at a low dosage.

SCONA TPPP 9212 GA improves the mechanical properties of these compounds, especially in polypropylene natural fiber compounds. Here it also reduces water absorption.

In its supplied form (granulate), the modifier is highly suited to producing one-packs and masterbatches.

### Recommended Levels

0.5-2 % additive (as supplied) based on the total formulation, depending on the fiber/filler content.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

### Incorporation and Processing Instructions

Good wetting of the fibers/fillers is required for effective compounding. For this reason, the product must be added to the main feed.



Additive Guide



**BYK USA Inc.**  
524 South Cherry Street  
P.O. Box 5670  
Wallingford, CT 06492  
USA  
Tel 203 265-2086  
Fax 203 284-9158

[cs.usa@byk.com](mailto:cs.usa@byk.com)  
[www.byk.com](http://www.byk.com)

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents. This issue replaces all previous versions – Printed in the USA