

AQUACER 552

HDPE-based wax emulsion for improved scratch resistance in aqueous coatings and printing inks.

Product Data

Composition

Non-ionic emulsion of an oxidized HD polyethylene wax

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Non-volatile matter (60 min., 257 °F): 35 %
Carrier: Water
Melting point (wax content): 266 °F
Viscosity (73 °F, D=800/s): 25 mPa·s
pH value: 9

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Temperature sensitive. To be stored and transported between 5 °C (41 °F) and 35 °C (95 °F). Stir before use.

Applications

Coatings and Printing Inks

Special Features and Benefits

The additive improves the scratch resistance in aqueous systems.

Recommended Use

Aqueous Coating Systems	<input checked="" type="checkbox"/>
Aqueous Printing Inks	<input type="checkbox"/>

☒ especially recommended ☐ recommended

Recommended Levels

1-6 % additive (as supplied) based upon total formulation in aqueous coatings.

3-14 % additive (as supplied) based upon total formulation in aqueous printing inks.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive is preferably incorporated into the coating at the end of the production process with a low shear rate. Stir thoroughly before use.



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents. This issue replaces all previous versions – Printed in the USA