

BYK-P 9080

Processing additive for low-profile and class A SMC systems with mold release properties.

Product Data

Composition

Combination of surface-active substances and polymers

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Acid value: 77 mg KOH/g
Density (20 °C): 0.97 g/ml
Non-volatile matter (10 min., 150 °C): > 98%
Flash point: > 100 °C

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

To be stored and transported at a temperature below 40 °C. When storing below 0 °C, the product can thicken so that it is no longer possible to process it. After heating up to 20 °C and homogenizing, the product can be used again without any loss of effectiveness. Heating up in excess of 40 °C can cause a thickening that cannot be reversed.

Applications

SMC

Special Features and Benefits

BYK-P 9080 is a processing additive for low-profile and Class A SMC. It stabilizes the compound and improves the flow behavior. Due to its excellent mold release properties, it completely replaces traditional release agents. BYK-P 9080 brings about both an improved surface quality of the component as well as a better coating adhesion and adhesive bonding.

Einsatzempfehlungen

SMC (low-profile)	■
Class A SMC	■
SMC (low-shrink)	□

■ especially recommended □ recommended

Recommended Levels

4-5 % additive (as supplied) based on the total resin.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Incorporate whilst stirring after the UP resin and LS/LP components have become homogenized. Traditional release agents should be removed from the formulation. The additive has an influence on the thickening. An additional dosage of 10 % MgO may be required to achieve a thickening that is comparable to Zn/Ca-stearate systems.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYPK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany