

AQUACER 8026

Emulsion based on HD polyethylene wax for improving the surface properties of aqueous coating systems and printing inks.

AQUACER 8026 is only available in USA, Mexico and Canada

Product Data

Composition

Anionic emulsion of an oxidized high density polyethylene wax

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Non-volatile matter (ASTM D2834): 25 %
Carrier: Water
Melting point (wax component): 140 °C (284 °F)
Viscosity (25 °C, Brookfield DV-I): < 50 mPa·s
pH value (ASTM E70): 10

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Keep from freezing. To be stored and transported at a temperature between 5 °C (41 °F) and 35 °C (95 °F).

Applications

Coatings and Printing Inks

Special Features and Benefits

AQUACER 8026 improves slip, abrasion resistance (anti-scuff), mar resistance, offset resistance and is the additive of choice where rapid development of water resistance is required.

Recommended Use

The additive is recommended for aqueous coatings, printing inks and overprint varnishes.

Recommended Levels

1-2 % additive (as supplied) based upon total formulation for aqueous coatings.

5-10 % additive (as supplied) based upon total formulation for water based printing inks.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive should preferably be incorporated at the end of the production process at a low shear rate. Mix well before use.



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYPK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents. This issue replaces all previous versions – Printed in the USA