

AQUACER 497

Paraffin-based wax emulsion for aqueous coatings, printing inks as well as care products and polishes for improving water repellency and surface slip.

Product Data

Composition

Non-ionic aqueous emulsion of a paraffin wax

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Non-volatile matter: 50 %
Carrier: Water
Melting point (wax content): 140 °F
Viscosity (73 °F, D=800/s): < 50 mPa·s
pH value: 5.5

Food Contact Legal Status

The additive is suitable for applications that come into contact with food. For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Temperature sensitive. To be stored and transported between 5 °C (23 °F) and 35 °C (95 °F). Mix well before use.

Applications

Coatings and Printing Inks

Special Features and Benefits

The additive improves water repellency and anti-blocking in aqueous coatings; it also increases surface slip.

Recommended Use

Architectural coatings	■
Leather coatings	■
Printing inks and overprint varnishes	■

■ especially recommended

Recommended Levels

1-3 % additive (as supplied) based on the total formulation for coatings.

2-5 % additive (as supplied) based on the total formulation for printing inks.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive should preferably be added to the coating at the end of the production process using a low shear rate. Mix well before use.

Care Products and Polishes

Special Features and Benefits

AQUACER 497 increases gloss and improves polishability. After polishing, the paraffin wax provides protection against abrasion and marks on the treated surface. Weather resistance is improved.

The melting point of 60 °C means that AQUACER 497 can easily be polished up using a soft terry cloth or microfiber cloth without the use of mechanical tools.

Recommended Use

AQUACER 497 is used for maintaining and protecting coated surfaces as well as wood and metals.

Recommended Levels

1-25 % additive (as supplied) based on the total formulation.

A higher dosage is possible, however the polishability must be checked separately in this case. The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can be incorporated during any stage of the production process whilst stirring. In accordance with the formulation, abrasives and pigments should be used before the addition of the paraffin wax emulsion. Surface-active substances must be added at the end of the production process, as otherwise there is a tendency to foam during production.



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra. The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA