

DISPERPLAST-P

Wetting and dispersing additive for PVC plastisols for a better incorporation of pigments and to reduce sedimentation.

Product Data

Composition

Solution of an unsaturated polycarboxylic acid polymer

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Acid value: 180 mg KOH/g
Density (68 °F): 8.51 lbs/US gal
Refractive index (68 °F): 1.487
Flash point: 248 °F

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Separation or turbidity may occur at temperatures below 10 °C (50 °F). Warm to 20 °C (68 °F) and mix well. Do not exceed 50 °C (122 °F).

Applications

PVC Plastisols

Special Features and Benefits

The additive improves the color strength, minimizes floating and reduces the dispersion time. It also prevents any separation of the plasticizer and reduces settling.

Recommended Levels

Amount of additive (as supplied) based upon solids:

Inorganic pigments: 1-5 %
Organic pigments: 1-5 %
Carbon blacks: 3-5 %
Co-grind of pigments: 3 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive should be added to the liquid components prior to incorporating the solids.

DISPERPLAST-P

Data Sheet
Issue 03/2014



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com/additives

ACTAL®, ADJUST®, ADVITROL®, ALUFERSOL®, ANTI-TERRA®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CLAYTONE®, CLOISITE®, COPISIL®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, FULGEL®, FULMONT®, GARAMITE®, GELWHITE®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, NANOBYPK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, SILBYK®, TIXOGEL®, VISCOBYK®, Y-25®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.
This issue replaces all previous versions – Printed in the USA