

DISPERBYK-103

Wetting and dispersing additive for solvent-borne matting agent pastes.

Product Data

Composition

Solution of a copolymer with filler affinic groups

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C):	1.06 g/ml
Non-volatile matter (10 min., 150 °C):	40 %
Solvents:	Methoxypropylacetate
Flash point:	47 °C

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

At temperatures below 10 °C, DISPERBYK-103 has a tendency to cloud and separate. In this case, please heat the product to a temperature of approx. 35 °C and then stir.

Applications

Coatings Industry

Special Features and Benefits

The additive is used to produce highly concentrated matting agent pastes. Such pastes are fluid, stable upon storage, easy to utilize, and capable of being automatically dosed into the system. These matting agent pastes can also be post-added to adjust the degree of matting. The gloss reduction of matting agent pastes produced with DISPERBYK-103 may be lower than that of matting agents utilizing dry incorporation.

Recommended Use

Wood and furniture coatings	<input checked="" type="checkbox"/>
Industrial coatings	<input checked="" type="checkbox"/>
Protective coating systems	<input checked="" type="checkbox"/>
Architectural coatings	<input type="checkbox"/>

☒ especially recommended ☐ recommended

Recommended Levels

Amount of additive (as supplied) based upon pigment:

Inorganic pigments: 5-10 %
Titanium dioxide: 2-4 %
Matting agent: 30-60 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

For optimum performance, the additive must be incorporated into the millbase. Prepare paste resin, mix with the solvent and the additive, then add the matting agent. Example: Grinding resin (60 % solution), 30 parts; DISPERBYK-103, 12 parts; solvent, 40 parts; matting agent, 18 parts.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SCONA®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAC®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany