

GARAMITE 1210

Rheological Additive for Vinyl Ester and Unsaturated Polyester Resins

Product Data

Special Features and Benefits

GARAMITE 1210 is a unique rheological additive developed for vinyl ester and unsaturated polyester systems. GARAMITE 1210 is recommended for use in unsaturated polyester resins such as Orthophthalic, Isophthalic, DCPD and PET resins. Compared to fumed silica, GARAMITE 1210 provides improved sag (drainage) resistance, rheology control and stability, is more efficient and is easier to handle in manufacturing (less dusty, higher bulk density and not sensitive to shear).

Benefits

- Dispersion Ease
- Viscosity Stability
- Shear Stable
- Syneresis Prevention
- Gel Time Stability
- Settling Prevention
- Drainage/Sag Prevention
- Increased Efficiency

Recommended Levels

Because the recovery properties obtained with GARAMITE 1210 are unique, it is recommended application properties such as sag resistance or spray trials be used instead of viscosity to evaluate the efficiency of GARAMITE 1210. GARAMITE 1210 use levels are system dependent. A loading ladder from equal loading to 20-40 % less than fumed silica should be evaluated. Air release agents such as BYK-A 555* and rheological enhancers such as BYK-R 605* (typically added at 5-10 % based on the weight of GARAMITE 1210) are beneficial in many systems and should be included in the overall optimization evaluation.

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Color: Off White
Form: Fine Powder
Moisture Content: <6 %
Bulk Density: ~ 8 lbs/cu. ft. : ~ 130 kg/cu meter
Specific Gravity: 1.5-1.7

Incorporation and Processing Instructions

Incorporation procedures will vary based on the system being evaluated.

For epoxy and vinyl ester systems, the recommended incorporation procedure is to add GARAMITE 1210 to the resin under moderate to high shear. The addition of GARAMITE 1210 to the resin at a 1-6 % GARAMITE 1210 loading level may be required to achieve maximum efficiency during dispersion. If a solvent is available in the system, increased efficiency can typically be achieved by using the incorporation methods described below by replacing the styrene with the available solvent.

GARAMITE 1210

Data Sheet
Issue 10/2013

For unsaturated polyester resins, the recommended method of incorporation for maximum efficiency is to add GARAMITE 1210 directly into the styrene at 10-15 % solids. Styrene wets and disperses GARAMITE 1210 with only low shear agitation.

Methods for direct add to styrene include the following

- 1) Meter GARAMITE 1210 into the styrene line prior to the resin tank using an eductor.
- 2) Mix and/or recirculate GARAMITE 1210 and styrene through a recirculation pump or sonolator in the resin tank prior to resin addition.
- 3) Mix GARAMITE 1210 and styrene in a separate tank. Direct addition of GARAMITE 1210 into unsaturated polyester resins requires high shear mixing (4000 rpm) for proper dispersion. If you find it necessary to add GARAMITE 1210 directly to the resin, we recommend adding it to the resin at a 1-6 % GARAMITE 1210 loading to achieve maximum efficiency during dispersion.

BYK-Chemie GmbH

P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com/additives

ACTAL®, ADJUST-4®, ADVITROL®, BENTOLITE®, CLAYTONE®, CLOISITE®, COPISIL®, FULACOLOR®, FULCAT®, FULGEL®, FULMONT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PERMONT®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, SCP®, TIXOGEL®, Y25® are registered trademarks of BYK Additives.

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYPK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany