

BYK-R 607

Rheology additive for solvent-free and solvent-borne systems to enhance the rheological properties in conjunction with hydrophilic fumed silica and clay additives.

Product Data

Composition

Solution of amine functional oligoamides

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (68 °F): 8.18 lbs/US gal

Refractive index (68 °F): 1.517

Viscosity: 20000 mPa·s

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Applications

Ambient Curing Systems

Special Features and Benefits

BYK-R 607 is a rheology additive for the thixotropic enhancement of solid thixotropes e.g. hydrophilic fumed silica or clay additives. The additive reinforces the network developed by the thixotrope, ensuring that it does not break down, as it usually would, when the amine hardener is added. BYK-R 607 enables hydrophilic fumed silica or clay additives to be used alone in 2-component epoxy systems. When using BYK-R 607, it is not necessary to use hydrophobic fumed silica in epoxy resin and hydrophilic fumed silica in the curing agent to achieve very high layer thicknesses. The additive is added to the curing agent. The spontaneous increase in viscosity is achieved by the formation of hydrogen bonds between the thixotrope and the BYK-R 607. The formulator is now able to rely on inexpensive hydrophilic, pyrogenic fumed silica or clay additives, without having to compromise the application properties. This enables an automatic reduction in raw materials costs and improves the quality of the product.

Recommended Use

Epoxy resin systems	<input checked="" type="checkbox"/>
Polyurethane systems	<input type="checkbox"/>
Acrylate systems	<input type="checkbox"/>

☒ especially recommended ☐ recommended

Recommended Levels

20-80 % additive (as supplied), always based on the percentage of hydrophilic, pyrogenic fumed silica and clay additive in the system.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

It is recommended to add the BYK-R 607 additive to the amine hardener. If the utilized amine hardener also contains hydrophilic fumed silica or clay additive, this must be taken into consideration when calculating the amount of additive that is to be used.

Special Note

BYK-R 607 is effective only in combination with hydrophilic types of fumed silica and clay silicates. The quantity of additive to be added can vary depending on the amine hardener that is used.

Coatings Industry**Special Features and Benefits**

BYK-R 607 is a rheology additive for the thixotropic enhancement of solid thixotropes e.g. hydrophilic fumed silica or clay additives. The additive reinforces the network developed by the thixotrope, ensuring that it does not break down, as it usually would, when the amine hardener is added. BYK-R 607 enables hydrophilic fumed silica or clay additives to be used alone in 2-component epoxy systems. When using BYK-R 607, it is not necessary to use hydrophobic fumed silica in epoxy resin and hydrophilic fumed silica in the curing agent to achieve very high layer thicknesses. The additive is added to the curing agent. The spontaneous increase in viscosity is achieved by the formation of hydrogen bonds between the thixotrope and the BYK-R 607. The formulator is now able to rely on inexpensive hydrophilic, pyrogenic fumed silica or clay additives, without having to compromise the application properties. This enables an automatic reduction in raw materials costs and improves the quality of the product.

Recommended Use

Protective coatings	<input type="checkbox"/>
Architectural coatings	<input type="checkbox"/>
General industrial coatings	<input checked="" type="checkbox"/>

☒ especially recommended ☐ recommended

Recommended Levels

20-80 % additive (as supplied), always based on the percentage of hydrophilic, pyrogenic fumed silica and clay additive in the system.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

It is recommended to add the BYK-R 607 additive to the amine hardener. If the utilized amine hardener also contains hydrophilic fumed silica or clay additive, this must be taken into consideration when calculating the amount of additive that is to be used.

Special Note

BYK-R 607 is effective only in combination with hydrophilic types of fumed silica and clay additives. The quantity of additive to be added can vary depending on the amine hardener that is used.

Adhesives

Special Features and Benefits

BYK-R 607 is a rheology additive for the thixotropic enhancement of solid thixotropes e.g. hydrophilic fumed silica or clay additives. The additive reinforces the network developed by the thixotrope, ensuring that it does not break down, as it usually would, when the amine hardener is added. BYK-R 607 enables hydrophilic fumed silica or clay additives to be used alone in 2-component epoxy systems. When using BYK-R 607, it is not necessary to use hydrophobic fumed silica in epoxy resin and hydrophilic fumed silica in the curing agent to achieve very high layer thicknesses. The additive is added to the curing agent. The spontaneous increase in viscosity is achieved by the formation of hydrogen bonds between the thixotrope and the BYK-R 607. The formulator is now able to rely on inexpensive hydrophilic, pyrogenic fumed silica or clay additives, without having to compromise the application properties. This enables an automatic reduction in raw materials costs and improves the quality of the product.

Recommended Use

Reactive adhesives based on epoxy resins.

Recommended Levels

20-80 % additive (as supplied), always based on the percentage of hydrophilic, pyrogenic fumed silica and clay additive in the system.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

It is recommended to add the BYK-R 607 additive to the amine hardener. If the utilized amine hardener also contains hydrophilic fumed silica or clay additive, this must be taken into consideration when calculating the amount of additive that is to be used.

Special Note

BYK-R 607 is effective only in combination with hydrophilic types of fumed silica and clay additives. The quantity of additive to be added can vary depending on the amine hardener that is used.

BYK-R 607

Data Sheet
Issue 12/2013



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA