

BYK-SYNERGIST 2105

Pigment synergist for solvent-borne and solvent-free coating systems. Improves the effectiveness of polymeric wetting and dispersing additives when stabilizing organic yellow, orange and red pigments.

Product Data

Composition

Insoluble pigment complex

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (68 °F): 9.26 lbs/US gal
Non-volatile matter: 100 %
Melting point: 311 °F
Moisture content: 2 %
Supplied as: Powder

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Applications

Coatings Industry

Special Features and Benefits

The synergist enables high-molecular weight wetting and dispersing additives to be more efficiently adsorbed on the surface of organic yellow, orange and red pigments, thereby increasing the effectiveness of the wetting and dispersing additives. Stabilization of the pigments is improved and higher pigment contents are possible as a result of a reduction in the viscosity.

Recommended Use

The synergist is always used in combination with high-molecular weight wetting and dispersing additives and is recommended for coatings and pigment concentrates.

Recommended Levels

Additive dosage as supplied based on pigment:

Organic yellow pigments (e.g. PY 154, PY 110): 2-4 %

Organic orange pigments (e.g. PO 36, PO 62): 2-4 %

Organic red pigments (e.g. PR 179, PR 254): 3-5 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

For optimum performance, the powdered synergist must be incorporated in the millbase together with polymeric wetting and dispersing additives prior to adding the pigments.



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA