

BYK-S 750 N

Styrene emission suppressant for DCPD-containing unsaturated polyester resins and isophthalic and vinyl ester resins. The interlaminar adhesion of polyester resin laminates is not affected.

Product Data

Composition

Combination of waxes with polar components

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (104 °F): 7.09 lbs/US gal

Flash point: > 212 °F

Supplied as: Paste

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Temperature sensitive. To be stored and transported between 20 °C (68 °F) and 50 °C (122 °F). Separation or turbidity may occur during storage and transportation. Mix well before use.

Applications

Ambient curing resin systems

Special Features and Benefits

BYK-S 750 N has been specifically developed as an emission reducer for use in DCPD-containing resins in which BYK-S 740 is too soluble to create a surface film. BYK-S 750 N reduces the emission without any adverse effect on the interlaminar adhesion and also works very well in isophthalic resins and vinyl ester resins.

Recommended Levels

0.3-1 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

BYK-S 750 N must be stirred well before incorporating to ensure the homogeneity of the product. BYK-S 750 N should be added to the resin whilst stirring before adding other formulation components. To ensure that the optimum crystal structure of BYK-S 750 N is not affected, the product must not be melted.

Special Note

In non-thixotropic resins, BYK-S 750 N tends to flocculate and floats to the resin surface during storage. In the case of separation, the resin must be stirred before processing.

BYK-S 750 N

Data Sheet
Issue 07/2014



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABÉN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.
This issue replaces all previous versions – Printed in the USA