

Data Sheet Issue 09/2013

BYK-3155

Silicone-free polymer-based air release additive for PVC plastisols. Standard additive, all-purpose.

Product Data

Composition

Compound of polyoxyalkylene derivatives

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (68 °F): 9.43 lbs/US gal

Refractive index (68 °F): 1.456

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Applications

PVC Plastisols

Special Features and Benefits

The additive is recommended for releasing air from PVC plastisols and is all-purpose.

Recommended Use

Unfilled plastisols	
Filled plastisols	
Foamed plastisols	
Plastisols containing BBP/Mesamoll	
especially recommended recommended	

Recommended Levels

0.2-1 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

To prevent the formation of foam and bubbles during production and/or application, the air release additive should be mixed with the plasticizer during plastisol production.

BYK-3155

Data Sheet Issue 09/2013







BYK USA Inc.

524 South Cherry Street P.O. Box 5670 Wallingford, CT 06492 USA Tel 203 265-2086 Fax 203 284-9158

cs.usa@byk.com www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERBYK®, DISPERBYK®, DISPERBYK®, DISPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra. The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions - Printed in the USA