

# DISPERBYK-2001

Wetting and dispersing additive for solvent-borne automotive coatings to stabilize pigments in base coats which contain CAB. Particularly strong reduction in millbase viscosity. Increases the jetness of carbon blacks in automotive coatings.

## Product Data

### Composition

Solution of a structured acrylate copolymer with pigment-affinic groups


### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Amine value:	29 mg KOH/g	
Acid value:	19 mg KOH/g	
Density (20 °C):	1.03 g/ml	
Non-volatile matter (20 min., 150 °C):	46 %	
Solvents:	Methoxypropylacetate/butylglycol/methoxypropanol	2/2/1
Flash point:	35 °C	

### Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit [www.byk.com](http://www.byk.com) for further information.



## Applications

### Coatings Industry

#### Special Features and Benefits

DISPERBYK-2001 deflocculates pigments by means of steric stabilization. It also generates a uniform electrical charge in the pigment particles. The resulting repulsion effect and the steric stabilization prevent any coflocculation which leads to non-floating coloring in pigment blends. As a result of the small particle size of the deflocculated pigments, high levels of gloss can be achieved and the color strength is improved, transparency is increased in transparent pigments and hiding power is increased in opaque pigments. In the case of fine-particle carbon blacks, DISPERBYK-2001 produces a significant improvement in the jetness of carbon blacks. Moreover, the viscosity is reduced which improves the leveling properties and enables a higher pigment load. In many systems, the use of DISPERBYK-2001 produces an even greater reduction in the viscosity of the millbase than DISPERBYK-2000.

#### Recommended Use

DISPERBYK-2001 is particularly recommended for automotive coatings and is suitable for base coats containing CAB and all top coats. It prevents the reflocculation of the pigments even when CAB is added after grinding. For an outstanding grind result it is not necessary to use CAB in the grinding phase.

## Recommended Levels

Amount of additive (as supplied) based upon pigment:

Inorganic pigments:	10-15 %
Titanium dioxides:	5 %
Organic pigments:	15-60 %
Carbon blacks:	70-140 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

## Incorporation and Processing Instructions

For optimum performance, the additive must be incorporated into the millbase before addition of pigments. Pre-mix the resin and solvent components of the millbase and then gradually let the additive flow in whilst stirring. Only add the pigments when the additive has been thoroughly distributed. In less polar binder solutions, adding DISPERBYK-2001 produces a brief increase in viscosity. This is product-specific and has no influence on the final dispersing result. The brief increase in viscosity can be prevented by adding small quantities of polar solvent (such as an alcohol or glycol) either to the additive or to the millbase.



Additive Guide



**BYK-Chemie GmbH**  
P.O. Box 10 02 45  
46462 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

[info@byk.com](mailto:info@byk.com)  
[www.byk.com/additives](http://www.byk.com/additives)

ACTAL®, ADJUST®, ADVITROL®, ALUFERSOL®, ANTI-TERRA®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CLAYTONE®, CLOISITE®, COPISIL®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, FULGEL®, FULMONT®, GARAMITE®, GELWHITE®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, NANOBYPK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, SILBYK®, TIXOGEL®, VISCOBYK®, Y-25®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany