

NANOBYK-3600

Nanoparticle dispersion (aluminum oxide) to improve the scratch resistance of aqueous, radiation curable coatings.

Product Data

Composition

Aluminum oxide nanoparticle dispersion

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (68 °F):	13.02 lbs/US gal
Non-volatile matter (10 min., 302 °F):	55 %
Carrier:	Water
Nanoparticle content:	50 %
Particle size D50:	40 nm
Viscosity (68 °F):	25 mPa·s

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

To be stored and transported between 5 °C (41 °F) and 40 °C (104 °F). Separation or turbidity may occur during storage and transportation. Mix well before use.

Special Note

The product must be stirred thoroughly before processing. Dried additive residues must be removed from the container since they can lead to seeding when introduced into the final product.

Applications

Coatings Industry

Special Features and Benefits

The additive improves the scratch resistance of coating surfaces and is particularly recommended for aqueous, radiation-curable parquet and furniture coatings. Even low levels of 1.0-5.0 % of the additive considerably improve the scratch resistance without having a significant impact on the optical properties such as gloss, color, transparency and other physical properties.

Recommended Levels

1.0-5.0 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The product reaches its full effectiveness when added at low shear forces. This ensures that even distribution in the binder system is achieved.

Special Note

NANOBYK-3600 can be combined with silicone-containing surface additives. For radiation-curable systems we therefore recommend using NANOBYK-3600 in conjunction with, for example, BYK-UV 3500, BYK-UV 3505, BYK-UV 3510 or BYK-UV 3575. For non-radiation-curable systems we recommend NANOBYK-3600 in conjunction with, for example, BYK-307, BYK-333 or BYK-378.



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA