

Data Sheet Issue 03/2015

CERAFLOUR 932 G

LDPE-based wax additive to improve the processing of rigid and flexible PVC as well as for matting and improving the surface characteristics of powder coatings.

Product Data

Composition

Modified polyethylene wax (LDPE)

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (68 °F): 7.76 lbs/US gal

Melting point: 221 °F Supplied as: Granulate

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Temperature sensitive. To be stored and transported at a temperature below 50 °C (122 °F).

Applications

PVC

Special Features and Benefits

The additive reduces the adhesion of the polymer melt on the calender roll. It accelerates the gelling of rigid PVC and acts as an external lubricant. CERAFLOUR 932 G is suitable for rigid and flexible PVC.

Recommended Levels

0.2-2 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive is added to the PVC granulate whilst stirring (at medium speed) and prior to calendering.

CERAFLOUR 932 G

Data Sheet Issue 03/2015

Powder Coatings

Special Features and Benefits

The additive is recommended for matting powder coatings and it also improves surface slip and surface protection.

Recommended Use

CERAFLOUR 932 G is recommended for powder coatings based on polyester/TGIC/primid/powder link, polyester/epoxy, acrylate, polyurethane and epoxy.

Recommended Levels

0.5-2 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive should be mixed with resin, hardener, pigments and other additives using a high-speed mixer and extruded along with all the components.







BYK USA Inc. 524 South Cherry Street P.O. Box 5670 Wallingford, CT 06492 Tel 203 265-2086 Fax 203 284-9158

cs.usa@byk.com www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives.

AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents. This issue replaces all previous versions – Printed in the USA