


DISPERBYK-2013

Solvent-free wetting and dispersing additive for 100 % UV systems and solvent-borne and water-borne UV systems for printing inks and coatings.



Product Data

Composition

Structured copolymer with pigment affinic groups

Solvent-free

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Amine value:	18 mg KOH/g
Acid value:	8 mg KOH/g
Density (68 °F):	9.18 lbs/US gal
Non-volatile matter (30 min., 302 °F):	> 98.5 %
Flash point:	> 302 °F

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Applications

Printing Inks

Special Features and Benefits

Based on its balanced product polarity and 100 % delivery form, DISPERBYK-2013 achieves excellent stabilization, in particular in 100 % UV systems and particularly of organic pigments and carbon black pigments. In so doing, DISPERBYK-2013 has an impressive, effective viscosity-reducing effect, simultaneously reducing thixotropic flow behavior. The long-term storage stability of printing inks formulated using DISPERBYK-2013 is also significantly improved. The highly deflocculating effect of this wetting and dispersing additive makes it possible to formulate printing inks with superior optical properties. The improvement in the color strength and transparency is particularly significant.

Recommended Use

UV-curable printing inks and pigment concentrates	■
---	---

■ particularly recommended

DISPERBYK-2013

Data Sheet
Issue 06/2013

Recommended Levels

Additive dosage as supplied based on pigment:

Organic pigments: 15-25 %
Carbon blacks: 15-25 %

The above recommended levels can be used for orientation. Optimal dosage levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The wetting and dispersing additives should be incorporated into the millbase. The additive should be premixed in the binder or solvent before the pigment is added.

Coatings Industry

Special Features and Benefits

Based on its balanced product polarity and 100 % delivery form, DISPERBYK-2013 achieves excellent stabilization in 100 % and solvent-borne and aqueous UV systems, in particular excellent stabilization of organic pigments and carbon black pigments. In so doing, DISPERBYK-2013 has an impressive, effective viscosity-reducing effect, simultaneously reducing thixotropic flow behavior. The long-term storage stability of coating systems formulated using DISPERBYK-2013 is also significantly improved. The highly deflocculating effect of this wetting and dispersing additive makes it possible to formulate coating systems with superior optical properties. The improvement in the color strength and transparency, combined with increased gloss and reduced haze is particularly significant.

Recommended Use

Industrial coatings	■
Wood and furniture coatings	■

■ particularly recommended

Recommended Levels

Additive dosage as supplied based on pigment:

Inorganic pigments: 2-8 %
Organic pigments: 15-35 %
Carbon blacks: 30-60 %

Incorporation and Processing Instructions

The wetting and dispersing additives should be incorporated into the millbase. The additive should be homogenized in the binder, solvent or reactive thinner before the pigment is added.



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra. The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA