

BYK-3441

Polyacrylate-based surface additive for solvent-borne and aqueous systems to improve leveling.

Product Data

Composition

Solution of an acrylate copolymer

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (68 °F):	8.53 lbs/US gal
Non-volatile matter (10 min., 302 °F):	52 %
Solvents:	Dipropylene glycol monomethyl ether
Flash point:	167 °F

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Special Note

The additive contains C₆F₁₃ fluorotelomers and replaces BYK-380 N.

Applications

Coatings Industry

Special Features and Benefits

BYK-3441 is an acrylate leveling additive that also reduces the surface tension and therefore improves substrate wetting and prevents cratering and pinholes. The additive is recommended for solvent-borne and aqueous systems.

Recommended Levels

0.1-1 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can be incorporated during any stage of the production process, including post-addition.

Special Note

The recoatability and intercoat adhesion should be tested when used in systems which are baked in excess of 150 °C (302 °F).

Adhesives & Sealants**Special Features and Benefits**

BYK-3441 is an acrylate leveling additive that also reduces the surface tension and therefore improves substrate wetting and prevents cratering and pinholes. The additive is recommended for aqueous adhesive systems, but can also be used in solvent-borne systems.

Recommended Levels

0.1-1 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can be incorporated during any stage of the production process, including post-addition.



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA