

DISPERBYK-111

Solvent-free wetting and dispersing additive for solvent-borne and solvent-free coatings and printing inks for stabilizing inorganic pigments, in particular titanium dioxide.
Strong reduction of millbase viscosity.

Product Data

Composition

Copolymer with acidic groups

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Acid value: 129 mg KOH/g

Density (20 °C): 1.16 g/ml

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Mix well before use. Separation and turbidity may occur. Heat to 30-40 °C and stir.

The product should be stored in closed rooms and should not be pre-diluted upon storage.

Special Note

As a result of its high acid value, the additive may potentially accelerate the reaction of baking systems. Check the increase in viscosity during storage.

Applications

Coating Industry and Printing Inks

Special Features and Benefits

The additive deflocculates pigments by means of steric stabilization. As a result of the small particle sizes of the deflocculated pigments, high levels of gloss can be achieved and the color strength is improved. Transparency and hiding power also increase and viscosity is reduced. In this way, the flow characteristics are also improved and high pigment loading is possible. For inorganic pigmented coatings, which are applied using electrostatic high rotation equipment, haze is significantly reduced.

Recommended Use

The additive is recommended for all solvent-borne and solvent-free coatings and printing inks to stabilize inorganic pigments, specifically titanium dioxide. Its anionic character makes it ideal for acid-catalyzed systems (e.g. coil coatings).

Recommended Levels

Amount of additive (as supplied) based upon pigment:

Inorganic pigments: 2.5-5 %

Titanium dioxides: 1-3 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

For optimum performance, the additive must be incorporated into the millbase before addition of pigments.



Additive Guide



BYK-Chemie GmbH
Postfach 10 02 45
46462 Wesel
Deutschland
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SCONA®, SILBYK®, VISCOBYK® und Greenability® sind eingetragene Warenzeichen der BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL® und VISCOSEAL® sind eingetragene Warenzeichen der BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER® und MINERPOL® sind eingetragene Warenzeichen der BYK-Cera.

Die vorstehenden Angaben entsprechen unserem derzeitigen Kenntnisstand. Sie beschreiben abschließend die Beschaffenheit unserer Produkte, stellen jedoch keine Garantie im Rechtssinne dar. Vor der Verwendung unserer Produkte obliegt es dem Verwender, die Qualität und Eignung unserer Produkte für die von ihm geplante Verarbeitung und Anwendung zu prüfen. Dies gilt auch für eine etwaige Verletzung von Schutzrechten Dritter. Wir behalten uns Änderungen der vorstehenden Angaben aufgrund technischen Fortschritts und betrieblicher Weiterentwicklungen vor. Diese Ausgabe ersetzt alle bisherigen Versionen – Gedruckt in Deutschland