

BYK-SILCLEAN 3720

Silicone-containing surface additive for aqueous coating systems to improve the easy-to-clean effect. Hydroxy-functional. Permanent effect after cross-linking.

Product Data

Composition

Solution of polyether-modified, hydroxy-functional polydimethylsiloxane.

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C):	0.95 g/ml
Non-volatile matter (10 min., 150 °C):	25 %
Solvents:	Methoxypropanol
Flash point:	31 °C
OH value (active substance):	29 mg KOH/g

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

To be stored and transported between 0 °C and 40 °C.

Applications

Coatings Industry

Special Features and Benefits

Due to its high surface activity, the additive accumulates on the surface of the coating where, on account of its OH reactivity, it can be integrated in the polymer network by reacting with suitable binders. If the additive is fixed to the coating surface via its reactive groups, the properties, which are caused by the use of the additive, are maintained for a long period of time.

In a multitude of coating systems, BYK-SILCLEAN 3720 increases the hydrophobic and oleophobic properties, which can significantly improve the water- and oil-repelling behavior. Moreover, it brings about a reduced dirt adhesion with a simultaneously increased easy-to-clean effect. The additive increases substrate wetting, leveling, surface slip, water resistance (blush resistance), anti-blocking properties and weather resistance. Therefore, we recommend that BYK-SILCLEAN 3720 is initially evaluated in the formulation without using other surface additives. If additional leveling is required, leveling additives can be added in a second step. BYK-SILCLEAN 3720 can also be used to improve anti-graffiti and tape release properties.

Recommended Use

BYK-SILCLEAN 3720 is hydroxyl-functional and is recommended for use in aqueous top coats. The following binder systems are particularly suitable for anchoring the additive in the binder matrix: 2-pack polyurethane, alkyd/melamine, polyester/melamine, acrylate/melamine and acrylate/epoxy combinations.

Recommended Levels

2-6 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive should be added towards the end of the production process and incorporated in the coating at a sufficient shear rate.

Special Note

If using the additive in applications where it is cross-linked with the binder, it is important that the coating is evenly and thoroughly sanded before recoating or retouching in order to ensure sufficient adhesion.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYPK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany