

Data Sheet Issue 10/2012

# **DISPERBYK-110**

Wetting and dispersing additive for solvent-borne and solvent-free coatings and printing inks for stabilizing inorganic pigments, in particular titanium dioxide. Strong reduction of millbase viscosity.

# **Product Data**

### Composition

Solution of a copolymer with acidic groups

### **Typical Properties**

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Acid value: 53 mg KOH/g Density (68 °F): 8.55 lbs/US gal

Non-volatile matter (10 min., 302 °F): 52 %

Solvents: Methoxypropylacetate/Alkylbenzenes 1/1

Flash point: 108 °F

# **Food Contact Legal Status**

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

### **Storage and Transportation**

Mix well before use. Separation and turbidity may occur. Heat to 30-40 °C (86-104 °F) and stir.

### **Special Note**

As a result of its high acid value, the additive may potentially accelerate the reaction of baking systems. Check the increase in viscosity during storage.

# **Applications**

### **Coating Industry and Printing Inks**

### **Special Features and Benefits**

The additive deflocculates pigments by means of steric stabilization. As a result of the small particle sizes of the deflocculated pigments, high levels of gloss can be achieved and the color strength is improved. Transparency and hiding power also increase and viscosity is reduced. In this way, the flow characteristics are also improved and higher pigment loading is possible. For inorganic pigmented coatings, which are applied using electrostatic high rotation equipment, haze is significantly reduced.

#### **DISPERBYK-110**

Data Sheet Issue 10/2012

### **Recommended Use**

The additive is recommended for all solvent-borne and solvent-free coatings and printing inks to stabilize inorganic pigments, specifically titanium dioxide. Its anionic character makes it ideal for acid-catalyzed systems (e.g. coil coatings).

### **Recommended Levels**

Amount of additive (as supplied) based upon pigment:

Inorganic pigments: 5-10 % Titanium dioxides: 2-4 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

# **Incorporation and Processing Instructions**

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.