

AQUACER 537

Paraffin wax emulsion for improved surface characteristics in aqueous coating systems.

Product Data

Composition

Anionic emulsion of a modified paraffin wax

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Non-volatile matter:	30 %
Carrier:	Water
Melting point:	110 °C
Viscosity (23 °C, D=400/s):	40 mPa·s
pH value:	9.5

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Temperature sensitive. To be stored and transported between 5 °C and 35 °C.
Mix well before use.

Applications

Coatings Industry

Special Features and Benefits

The additive has a hydrophobic effect in aqueous coatings. It improves antiblocking and increases surface slip.

Recommended Use

Furniture and parquet coatings	<input type="checkbox"/>
Architectural coatings	<input type="checkbox"/>

☐ recommended

Recommended Levels

1.5-5 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive should preferably be incorporated into the coating at the end of the production process at a low shear rate. Mix well before use.

AQUACER 537

Data Sheet
Issue 08/2013



Additive Guide



Google play

BYK-Chemie GmbH

P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany