

BYK-425

Liquid, VOC-free rheology additive for aqueous systems to set the in-can viscosity and to improve the anti-sagging and anti-settling properties.

Product Data

Composition

Solution of a urea-modified polyurethane

APEO-free
VOC-free

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Active substance: 50 %
Density (20 °C): 1.04 g/ml
Refractive index (20 °C): 1.46
Solvents: Polypropylene glycol
Flash point: > 100 °C

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

It is preferable to store BYK-425 at temperatures between 20 °C and 50 °C. Depending on the storage conditions, the additive can appear non-homogeneous; there is no known influence on the rheological effectiveness. Mix well before use.

Applications

Coatings, Printing Inks, and Adhesives

Special Features and Benefits

The rheological effectiveness of BYK-425 is primarily based on the associative interaction with the dispersion particles of the aqueous binder and enables a highly pronounced pseudoplastic flow behavior. The urea modification of the additive also causes an increase in the rheological effect via hydrogen bonds. BYK-425 is VOC- and APEO-free, does not impair gloss, and its rheological effect is not dependent on the pH value.

Recommended Use

BYK-425 is suitable for all kinds of aqueous coatings, printing inks, and adhesives in order to improve the anti-sagging properties and set the required in-can viscosity of the formulation. The resulting increase in viscosity simultaneously improves the storage stability with reduced settling. When grinding pigment pastes, the additive can also increase the millbase viscosity and therefore improve the dispersion conditions.

For formulations with a considerably lower application viscosity (e.g. coatings for conventional spraying), it is recommended to use BYK-425 together with BYK-420 (or BYK-D 420 or BYK-7420 ES), as the anti-settling properties are much more pronounced.

Recommended Levels

0.1-2 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

BYK-425 can be added to the formulation at any time during the production process; we recommend that it is post-added using a moderate shear force. If BYK-425 is to be used in pigment pastes to improve the dispersion conditions by increasing the millbase viscosity, it must be added directly to the millbase.

Due to its considerable rheological effectiveness, the additive may cause an immediate, very strong increase in viscosity and therefore make further processing more difficult. In this case, we recommend that it is prediluted. It can be diluted with just water (10 parts BYK-425 + 90 parts water) or also with a water/co-solvent mix using a standard coalescent (e.g. 20 parts BYK-425 + 70 parts water + 10 parts coalescent). BYK-425 is highly viscous at low temperatures; predilution can also be helpful under these conditions. The storage stability of the diluted solutions should be tested on a case-by-case basis.

Detergents, Cleaning and Care Products

Special Features and Benefits

The rheological effectiveness of BYK-425 is based on associative interactions with the surfactant micelles in the system, and enables a highly pronounced pseudoplastic flow behavior. Furthermore, the urea modification of the additive causes an increase in the rheological effect via hydrogen bonds. The resulting flow behavior is ideal, for example, for preventing particles (e.g. encapsulated fragrances) from settling, without negatively impacting the residual emptying of the container.

BYK-425 is VOC and APEO-free. The additive is liquid and therefore easy to handle. Its thickening effect is not dependent upon the pH value. The anti-settling properties are more pronounced at pH values above 4.5. The compatibility with surfactants, including cationic surfactants, is extremely good. The rheological effectiveness of the associative thickener depends on the respective system composition. The transparency of the application systems is preserved.

Recommended Use

BYK-425 is used as a thickener and anti-settling additive in aqueous systems.

Fabric softeners	<input checked="" type="checkbox"/>
------------------	-------------------------------------

☒ especially recommended ☐ recommended

Recommended Levels

0.1-1.0 % additive (as supplied) based upon the total formulation, depending on the properties of the formulation to be achieved.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

BYK-425 can be added to the formulation at any time during the production process; we recommend that it is post-added using a moderate shear force.

Due to its considerable rheological effectiveness, the additive can cause an immediate, very strong increase in viscosity and therefore make further processing more difficult. In this case, we recommend prediluting with water (10 parts BYK-425 to 90 parts water). BYK-425 is highly viscous at low temperatures; predilution can also be helpful under these conditions. The storage stability of the diluted solutions should be tested on a case-by-case basis.

BYK-425

Data Sheet
Issue 12/2016



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYPK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PRIEX®, PURE THIX®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25® **are registered trademarks of the BYK group.**

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany