

BYK-1723

VOC-free silicone-containing defoamer for aqueous architectural coatings, and adhesives. Preferably used in dispersion systems within a PVC range of 30-50. Cost-effective alternative to mineral oil defoamers.

Product Data

Composition

Emulsion of foam-destroying polysiloxanes, hydrophobic solids and emulsifying agents

VOC-free (< 1500 ppm)
Does not contain
alkylphenol ethoxylates

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C): 1.00 g/ml
Non-volatile matter (60 min., 105 °C): 18.5 %
Carrier: Water

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

To be stored and transported between 0 °C and 40 °C. Temperature-sensitive emulsion. If the storage temperature drops below or exceeds that recommended, the product should be checked and, if necessary, re-emulsified at room temperature.

Applications

Coatings Industry

Special Features and Benefits

BYK-1723 is a very versatile defoamer for aqueous systems. The additive is especially recommended for use in the production and application of emulsion paints and plasters within a PVC range of 30-50. BYK-1723 is VOC-free and can replace mineral oil defoamers.

Recommended Levels

0.1-0.5 % additive (as supplied) based on the total formulation – in exceptional cases up to 0.8 %.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can be added at any time during production. Sufficiently high shear forces must be applied.

Adhesives

Special Features and Benefits

BYK-1723 can be used in all aqueous dispersion adhesives as a defoamer.

Recommended Levels

0.05-0.5 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive can be incorporated during any stage of the production process, at low to moderate shear rates.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SCONA®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAC®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions – Printed in Germany