

CERAFLOUR 915

Micronized polypropylene wax for solvent-borne and aqueous systems, to achieve medium surface textures.

Product Data

Composition

Micronized polypropylene wax

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density: 0.9 g/ml
Melting point: 320 °F
Particle size distribution (laser diffraction, volume distribution): D50: 34 µm D90: 57 µm

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Temperature sensitive. To be stored and transported at a temperature below 50 °C (122 °F).

Applications

Coatings Industry

Special Features and Benefits

CERAFLOUR 915 generates a uniform and easily reproducible texture effect with a medium surface texture in aqueous and solvent-borne coating systems.

Recommended Use

Industrial coatings	■
Coil coatings	■
Wood and furniture coatings	■

■ especially recommended

Recommended Levels

1-10 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive is preferably incorporated at the end of the production process at a moderate shear rate.



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA