

DISPERBYK-190

VOC and solvent-free wetting and dispersing additive for aqueous coating systems, printing inks and adhesives. Standard additive for binder-free pigment concentrates. Suitable for all pigments.

Product Data

Composition

Solution of a high molecular weight block copolymer with pigment affinic groups

VOC-free
(< 1500 ppm)

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Acid value:	10 mg KOH/g
Density (68 °F):	8.85 lbs/US gal
Non-volatile matter (10 min., 302 °F):	40 %
Solvents:	Water

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Separation or turbidity may occur during storage or transportation below 0 °C (32 °F). Heat to 20 °C (68 °F) and stir.

Applications

Printing Inks

Special Features and Benefits

The additive deflocculates pigments by means of steric stabilization. As a result of the small particle sizes of the deflocculated pigments, high levels of gloss can be achieved and the color strength is improved. The transparency is also increased and the viscosity is reduced. In this way, the flow characteristics are also improved and higher pigment loading is possible.

Recommended Use

The additive is especially suitable for producing binder-free, stable pigment concentrates with a pigment content of 30-60 %. These pigment concentrates can be let down with standard aqueous binders, for example acrylate dispersions or water-soluble acrylic resins.

Recommended Levels

Amount of additive (as supplied) based upon pigment:

Titanium dioxides:	10-12 %
Organic pigments, Carbon blacks:	15-50 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Grinding should only take place in water (without binders, amines or co-solvents). Mix the additive with water and only add the pigments once the additive has been homogeneously and uniformly distributed.

Coatings Industry**Special Features and Benefits**

The additive deflocculates pigments by means of steric stabilization. As a result of the small particle sizes of the deflocculated pigments, high levels of gloss can be achieved and the color strength is improved. Transparency and hiding power are also increased and viscosity is reduced. In this way, the flow characteristics are also improved and higher pigment loading is possible.

Recommended Use

Architectural coatings	■
Wood and furniture coatings	■
Automotive coatings	■
Can coatings	■
Protective coatings	■
Leather finishes	■

■ especially recommended

The additive is recommended for producing binder-free, stable pigment concentrates for aqueous coatings without flooding/floating.

Recommended Levels

Amount of additive (as supplied) based upon pigment:

Inorganic pigments: 20-30 %
Titanium dioxides: 10-12 %
Organic pigments: 30-75 %
Carbon blacks: 130-150 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Grinding should only take place in water (without binders, amines or co-solvents). Mix the additive with water and only add the pigments once the additive has been homogeneously and uniformly distributed.

Adhesives

Special Features and Benefits

The additive improves the dispersion quality of fillers and pigments. By means of steric stabilization it deflocculates the pigments and fillers and reduces viscosity. In this way, the flow characteristics are also improved and higher pigment loading is possible.

Recommended Use

Aqueous adhesives	<input checked="" type="checkbox"/>
Epoxy systems	<input type="checkbox"/>
PUR systems	<input type="checkbox"/>

☒ especially recommended ☐ recommended

The additive is particularly recommended if the fillers and pigments are to be dispersed directly in water without binders.

Recommended Levels

Amount of additive (as supplied) based upon pigment:

Inorganic pigments: 20-30 %
Titanium dioxides: 10-12 %
Organic pigments: 30-75 %
Carbon blacks: 130-150 %
Fillers: 1-3 %

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Dispersion should only take place in water (without binders, amines or co-solvents). Mix the additive with water and only add the fillers and pigments once the additive has been homogeneously and uniformly distributed.

DISPERBYK-190

Data Sheet
Issue 10/2012

BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA