

BYKETOL-WS

Silicone-free surface additive for aqueous coatings to prevent surface defects such as cratering, scarring, bubbles, pinholes, orange peel and boiling marks and to improve leveling.

Product Data

Composition

Combination of surface-active, low-molecular-weight polymers

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (20 °C):	0.76 g/ml
Non-volatile matter (10 min., 150 °C):	4 %
Solvents:	Butylglycol
Flash point:	67 °C

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Separation or turbidity may occur at temperatures below 5 °C. Warm to 20 °C and mix well.

Applications

Coatings Industry

Special Features and Benefits

The additive is a leveling additive with defoaming properties. It prevents the formation of bubbles and boiling marks in aqueous baking coatings. Surface defects, such as cratering and pinholes, are avoided.

Recommended Levels

0.3-3 % additive (as supplied) based on the total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive should be incorporated into the millbase. Post-addition in the finished coating is also possible if sufficient shear forces are used.



Additive Guide



BYK-Chemie GmbH
P.O. Box 10 02 45

46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany