

NANOBYK-3810

Nanoparticle dispersion (cerium oxide) for long-term UV protection in aqueous systems.

Product Data

Composition

Cerium oxide nanoparticle dispersion

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density (68 °F):	10.13 lbs/US gal
Non-volatile matter (20 min., 302 °F):	23 %
Carrier:	Water
Nanoparticle content:	18 %
Particle size D50:	10 nm

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Storage and transport between 5 °C (41 °F) and 40 °C (104 °F). Separation may occur. Stir before use.

Applications

Coatings Industry

Special Features and Benefits

The cerium oxide nanoparticles dispersed in this additive provide long-term UV protection and stabilize the coating film to prevent fading and degradation. Gloss and transparency are not impacted due to the small size of the nanoparticles. Use in combination with organic radical scavengers (HALS) is recommended.

Recommended Use

The additive is particularly recommended for use in aqueous architectural coatings for wood care applications.

Recommended Levels

4-8 % additive (as supplied) based upon a solid binder.

The above recommended levels can be used for orientation. Optimal dosage levels are determined through a series of laboratory tests. The optimal dosage level of UV absorber is dependent on the layer thickness of the coating film. Thin layers require higher dosage levels while lower dosage levels are sufficient for thick layered systems.

Incorporation and Processing Instructions

The product reaches its full effectiveness when added at low shear forces. This ensures that even distribution in the binder system is achieved.

Special Note

The product must be stirred thoroughly before processing. Dried additive residues must be removed from the container since they can lead to seeding when introduced into the final product.



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.
This issue replaces all previous versions – Printed in the USA