

OPTIBENT-6042

Powdered rheology additive based on an organically modified phyllosilicate for aqueous, hydraulically hardening construction systems.

Product Data

Composition

Modified phyllosilicate

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Bulk density: 500-700 kg/m³
Moisture content: max. 14%
Supplied as: free-flowing, beige powder

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

The product is slightly hygroscopic and should be transported and stored dry in the unopened original container at temperatures between 0 °C (32 °F) and 30 °C (86 °F).

Applications

Construction industry

Special Features and Benefits

As a result of its extremely thixotropic properties, OPTIBENT-6042 develops high anti-sagging properties whilst retaining good processing properties and improved open times, even with greatly increased levels of water. Consequently, OPTIBENT-6042 makes it possible to increase the water required in mineral binder systems and improves the processing consistency without impairing the hydration properties of the binder system. The product is shear stable and compatible with a variety of cementitious binders.

Recommended Use

OPTIBENT-6042 is suitable for aqueous mineral binder systems, preferably for tile adhesive formulations for large tiles and other thin-layered applications.

Tile adhesive	<input checked="" type="checkbox"/>
ETICS/adhesives and reinforcement mortars	<input checked="" type="checkbox"/>
Thick-layer plasters	<input type="checkbox"/>

☒ especially recommended ☐ recommended

Recommended Levels

0.1-0.5 % additive (as supplied) based upon the total formulation, depending on the properties of the formulation to be achieved.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

OPTIBENT-6042 is hydrophilic and can be added as supplied to dry mix mortar formulations.



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PRIEX®, PURE THIX®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25®
are registered trademarks of the BYK group.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA