

OPTIGEL-CG

Rheology additive based on an activated phyllosilicate for aqueous coating systems to generate thixotropic flow behavior.

Product Data

Composition

Activated phyllosilicate

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Specific density: 2,6 g/cm³
Bulk density: ca. 600 kg/m³
Moisture content: ca. 8 %
Supplied as: free-flowing, cream-colored powder

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

OPTIGEL-CG is hygroscopic and should be transported and stored dry in the unopened original container at temperatures between 0 °C (32 °F) and 30 °C (86 °F).

Applications

Coatings Industry

Special Features and Benefits

OPTIGEL-CG generates thixotropic flow behavior. It improves processability and storage stability as it is highly effective at preventing solids settling. In addition, it reduces the sagging after application which makes it possible to achieve greater layer thicknesses. OPTIGEL-CG is inorganic and stable to diluted acids and bases.

Recommended Use

OPTIGEL-CG is suitable for a variety of aqueous coating systems and particularly suitable for use in highly filled architectural coatings.

Architectural coatings	<input checked="" type="checkbox"/>
------------------------	-------------------------------------

☒ especially recommended ☐ recommended

Recommended Levels

0.1-3.0 % additive (as supplied) based upon the total formulation, depending on the properties of the formulation to be achieved.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

OPTIGEL-CG is hydrophilic and easy to incorporate in water. To ensure optimum distribution and the best possible effectiveness and reproducibility in applications, the additive must be added to water (20 °C ± 5 °C) slowly whilst stirring, and pre-dispersed at high shear forces for at least 20 minutes. OPTIGEL-CG should be fully hydrated before the remaining formulation components can be added to the dispersion. No wetting or dispersing additives are required to produce this dispersion. Ionic substances with potassium, calcium, magnesium or ammonium ions or acids should be added only after the additive has been fully dispersed.



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PRIEX®, PURE THIX®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25®
are registered trademarks of the BYK group.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA