

# CERAFLOUR 961

Highly effective wax additive for improved degassing of powder coatings on porous substrates.

## Product Data

### Composition

Micronized, modified polyethylene wax

### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density:	0.95 g/ml	
Melting point:	140 °C	
Particle size distribution (laser diffraction, volume distribution):	D50: 5 µm	D90: 11 µm
Supplied as:	Micropowder	

### Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit [www.byk.com](http://www.byk.com) for further information.

### Storage and Transportation

Temperature sensitive. To be stored and transported at a temperature below 50 °C.

## Applications

### Powder Coatings

#### Special Features and Benefits

The additive improves the degassing of powder coatings, which are applied to porous substrates. It reduces the formation of pinholes and air bubbles and optimizes scratch resistance.

#### Recommended Use

CERAFLOUR 961 is used in powder coatings based on polyester/TGIC/Beta-HAA/epoxy-functional glycidyl esters, polyester/epoxy, polyurethane, acrylate, and epoxy.

#### Recommended Levels

0.5-2 % additive (as supplied) based on the total formulation when extruding with all formulation components.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

#### Incorporation and Processing Instructions

The product should be mixed with the resin, hardener, pigments and other additives using a high-speed mixer and extruded along with all components.

# CERAFLOUR 961

Data Sheet  
Issue 01/2014



Additive Guide



## BYK-Chemie GmbH

P.O. Box 10 02 45  
46462 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

[info@byk.com](mailto:info@byk.com)  
[www.byk.com/additives](http://www.byk.com/additives)

ACTAL®, ADJUST®, ADVITROL®, ALUFERSOL®, ANTI-TERRA®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CLAYTONE®, CLOISITE®, COPISIL®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, FULGEL®, FULMONT®, GARAMITE®, GELWHITE®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, SILBYK®, TIXOGEL®, VISCOBYK®, Y-25®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany