

Data Sheet Issue 07/2013

CERAFLOUR 916

Micronized, modified HDPE wax/polymer mixture for solvent-borne and aqueous systems, to achieve medium to coarse surface textures.

Product Data

Composition

Micronized, modified HD polyethylene wax/polymer mixture

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Density: 0.99 g/ml Melting point: 275 °F

Particle size distribution (laser diffraction, volume distribution): D50: 46 µm D90: 82 µm

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Temperature sensitive. To be stored and transported at a temperature below 50 °C (122 °F).

Applications

Coatings Industry

Special Features and Benefits

CERAFLOUR 916 generates a uniform and easily reproducible structure effect with a medium to coarse surface texture in aqueous and solvent-borne coating systems.

Recommended Use

Industrial coatings	
Coil coatings	
Wood and furniture coatings	

especially recommended

CERAFLOUR 916

Data Sheet Issue 07/2013

Recommended Levels

1-10 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive is preferably incorporated at the end of the production process at a moderate shear rate.







BYK USA Inc. 524 South Cherry Street P.O. Box 5670 Wallingford, CT 06492

Tel 203 265-2086 Fax 203 284-9158

believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.