

AQUAMAT 272

Matting wax dispersion based on modified PE for aqueous coatings, as well as printing inks and overprint varnishes for improved surface protection.

Product Data

Composition

Dispersion of modified polyethylene wax

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Non-volatile matter (60 min., 257 °F):	55 %
Carrier:	Water
Melting point (wax content):	257 °F
Particle size (Hegman):	30 µm
Viscosity (73 °F, D=800/s):	< 500 mPa·s
pH value:	4

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Temperature sensitive. To be stored and transported between 5 °C / 41 °F and 35 °C / 95 °F. Stir before use.

Special Note

In opened containers, the additive can dry out on the inner wall of the container. Such dried-out additive residues can lead to defects in the final product, and so the additive must be homogenized and filtered prior to use.

Applications

Coatings Industry

Special Features and Benefits

The additive increases surface protection and has a matting effect.

Recommended Use

Architectural coatings	<input checked="" type="checkbox"/>
Wood and furniture coatings	<input checked="" type="checkbox"/>
Industrial coatings	<input checked="" type="checkbox"/>
Leather finishes	<input type="checkbox"/>

☒ especially recommended ☐ recommended

Recommended Levels

1-6 % additive (as supplied) based upon total formulation, depending on the desired degree of matting.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive is preferably incorporated into the coating at the end of the production process with a low shear rate. Stir well before use.

Printing Inks and Overprint Varnishes

Special Features and Benefits

The additive increases abrasion resistance, and has a matting effect.

Recommended Levels

1-2 % additive (as supplied) based upon total formulation.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive is preferably incorporated into the coating at the end of the production process with a low shear rate. Stir well before use.



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com/additives

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra. The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA