

BYK-W 9011

Wetting and dispersion additive for SMC, BMC, and pultrusion to reduce the viscosity of fillers and pigments in LP and LS systems as well as in highly filled epoxy formulations. Not suitable for cobalt-accelerated systems. For low-emission formulations. Cost-effective alternative to BYK-W 9010.

Product Data

Composition

Copolymer with acidic groups

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Acid value:	65 mg KOH/g
Density (68 °F):	9.26 lbs/US gal
Refractive index (68 °F):	1.465
Water content:	0.13 %
Active substance:	100 %

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Separation or turbidity may occur during storage and transportation. Warm to > 30 °C (50 °F) and mix well.

Special Note

BYK-W 9011 is not recommended for use in ambient curing, cobalt-accelerated resins because the curing process may be inhibited.

Applications

SMC, BMC, Pultrusion

Special Features and Benefits

BYK-W 9011 improves the wetting and dispersion of the most common fillers such as calcium carbonate and ATH (aluminum trihydroxide). The additive reduces viscosity which enables higher filler content. The improved wetting and dispersion of the fillers results in improved homogeneity and also optimizes batch reproducibility. In BMC formulations BYK-W 9011 is recommended for viscosity stabilization.

Recommended Use

BYK-W 9011 is solvent-free and particularly recommended for formulations in which solvents need to be avoided.

Low emission SMC/BMC	■
LP and Class A formulations	■
LS formulations	■
Pultrusion	■
Epoxy systems	□

■ especially recommended □ recommended

Recommended Levels

0.5-1 % additive (as supplied) based on fillers/pigments for wetting and dispersion.
0.25-1 % additive (as supplied) based on the resin in BMC for viscosity stabilization.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

The additive should be added to the resin mixture prior to homogenization and the addition of the fillers/pigments.



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.
This issue replaces all previous versions – Printed in the USA