

BYKJET-9142

Solvent-free wetting and dispersing additive to improve the dispersing and particle size distribution of inorganic pigments in low-polarity ceramic inkjet inks. The additive reduces the viscosity of the inkjet inks.

Product Data

Composition

Polymer with pigment affinic groups

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Acid value: 95 mg KOH/g
Active substance: 100 %
Density (68 °F): 8.43 lbs/US gal
Flash point: 367 °F

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

The product may solidify below 20 °C / 68 °F. Warm to 30-60 °C / 86-140 °F and mix well. Moisture sensitive.


Applications

Ceramic Inkjet Inks

Special Features and Benefits

BYKJET-9142 is a wetting and dispersing additive with a highly deflocculating effect that uses steric hindrance to prevent the reflocculation of pigments. It leads to a pronounced reduction in viscosity and Newtonian flow characteristics, which can increase the pigment content of the ink. Good long-term stability with respect to settling behavior and syneresis is also achieved. The product has a strong impact on particle size and leads to an even particle size distribution in pigment dispersions, thereby significantly shortening the filtration time. BYKJET-9142 can be used in low-polarity ceramic inkjet inks based on hydrocarbons and fatty acid esters. It can be used either as the only dispersing additive or in combination with other products. Good results with BYKJET-9142 are also obtained at low dosage.

Recommended Use

Ceramic inkjet inks	
---------------------	-------------------------------------------------------------------------------------

 especially recommended

Recommended Levels

5-30 % additive (as supplied) based on inorganic pigments.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Wetting and dispersing additives should generally be added to the millbase. This is the only way in which they can be fully effective. Pre-mix the solvent components of the millbase and then gradually pour in the additive while stirring. Add the pigments only after the additive has been thoroughly dispersed.



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. ACTAL®, ADJUST®, ADVITROL®, ASTRABEN®, BENTOLITE®, CLAYTONE®, CLOISITE®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, TIXOGEL®, and VISCOSEAL® are registered trademarks of BYK Additives. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAC®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera. SCONA® is a registered trademark of BYK Kometra.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents. This issue replaces all previous versions – Printed in the USA