

BYK-D 420

Liquid rheology additive for aqueous systems to generate thixotropic flow behavior.

Product Data

Composition

Solution of a modified urea

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Active substance: 45 %

Density (68 °F): 9.60 lbs/US gal

Solvents: Dimethyl sulfoxide

Flash point: 203 °F

Food Contact Legal Status

For the current food contact legal status, please contact our product safety department or visit www.byk.com for further information.

Storage and Transportation

Moisture sensitive. Store dry. Slight turbidity of the material that occurs during storage has no influence on the rheological effectiveness.

Applications

Coatings Industry

Special Features and Benefits

After being stirred into the coating system, the additive generates a three-dimensional network structure. The resulting thixotropic flow behavior is highly suited for preventing sedimentation and syneresis and increasing the anti-sagging properties without impairing leveling. The additive is liquid and therefore easy to handle. It is not necessary to specifically adjust the pH value or control the temperature during incorporation.

Recommended Use

BYK-D 420 is preferably used as an anti-settling additive to produce aqueous pigment, filler and matting agent concentrates. The additive's excellent shear thinning effect is advantageous for dosing such concentrates because of their low viscosity. In addition, it is suitable for controlling the thixotropic flow behavior and for optimizing the anti-sagging properties and leveling.

Recommended Levels

0.3-1.5 % additive (as supplied) based on the total formulation to prevent settling.

0.3-3 % to prevent sagging.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Addition into the millbase ensures optimum distribution and therefore the best possible effectiveness and reproducibility in applications. It is not necessary to specifically control the temperature or adjust the pH value. The additive is also suitable for retroactively adjusting the viscosity by incorporating it as a post-additive. If the use as a post-additive causes the product to appear non-homogeneous, typical co-solvents can be used to improve the homogeneity.

Special Note

As the additive contains chloride ions, we recommend testing the corrosion properties of the manufactured coatings for contact with metal and to store the coatings in plastic containers or containers with interior coating to prevent corrosion in metal containers. In the cured coating, however, no negative impact on its corrosion protection has been found.

Detergents, Cleaning and Care Products

Special Features and Benefits

After being incorporated into the system, the additive generates a three-dimensional network structure. The resulting thixotropic flow behavior is ideal for preventing particles (e.g. encapsulated fragrances) from settling, without negatively impacting the residual emptying of the container. Cleaning products with BYK-D 420 are easy to use and can be applied by spraying. The use of the additive improves adhesion to vertical surfaces, which improves the cleaning action as a result of the longer exposure time. The additive is liquid and therefore easy to handle. It is not necessary to specifically adjust the pH value or control the temperature during incorporation. BYK-D 420 is stable to acids and bases in a pH range of 0-13. The electrolyte resistance and compatibility with surfactants, including cationic surfactants, are excellent. The transparency of the detergents and cleaning products is preserved.

Recommended Use

BYK-D 420 is used as a rheology additive to improve the anti-sagging and anti-settling properties in aqueous detergents, cleaning and care products.

Acidic toilet cleaning products	<input checked="" type="checkbox"/>
Liquid detergents	<input type="checkbox"/>

☒ especially recommended ☐ recommended

Recommended Levels

0.3-3.0 % additive (as supplied) based upon the total formulation, depending on the properties of the formulation to be achieved.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

Incorporation and Processing Instructions

Addition under controlled stirring ensures optimum distribution and the best possible effectiveness and reproducibility in applications. It is not necessary to specifically control the temperature or adjust the pH value. The additive is also suitable for subsequently adjusting the viscosity by incorporating it as a post-additive. If this causes the product to appear non-homogeneous, typical water-miscible solvents (e.g. alcohols, ketones, glycols, esters) can be used to improve the homogeneity.

BYK-D 420

Data Sheet
Issue 12/2016



Additive Guide



BYK USA Inc.
524 South Cherry Street
P.O. Box 5670
Wallingford, CT 06492
USA
Tel 203 265-2086
Fax 203 284-9158

cs.usa@byk.com
www.byk.com

ACTAL®, ADD-MAX®, ADD-VANCE®, ADJUST®, ADVITROL®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKO2BLOCK®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERAL COLLOID®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PAPERBYK®, PERMONT®, PRIEX®, PURE THIX®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL®, VISCOBYK® and Y 25®
are registered trademarks of the BYK group.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty, either expressed or implied, is made or intended. Use by a customer should be based upon their own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

This issue replaces all previous versions – Printed in the USA